

# FASTRACK

## QUICK DRYING MARKING PAINT

### DESCRIPTION

A high quality quick drying water based Acrylic coating designed to provide a coloured demarcation system.



### USES

For use in lightly trafficked areas such as car parks, cycleways, walkways, central reservations and other areas requiring a coloured coating with good slip resistance.

> Can be spray, brush or roller applied.

**Old polished granite macadams and power floated concrete areas as well as chemically or mechanically hardened floors may not be suitable for coating.**

> Do not store outdoors

### SHELF LIFE

> Up to 6 months  
> Store above 5°C.

### COLOUR RANGE

> White, Yellow, Red, Blue and special colours are all made to order.

### PACK SIZE

> Available in 5 litre (7.5kg - approx) containers.

### SPREADING RATE

> As a guide, up to 4-6 square metres/litre dependent on substrate, texture and porosity of surface.  
> Apply 2 coats by spray, brush or roller.

### LINE MARKING PAINT

> As a guide the coverage is between 35-70 linear metres per litre at 50mm width, dependent on substrate, texture and porosity of the surface.

### DRYING TIME

> At 20°C tack free - 20 minutes.  
> Open traffic - 2 hours.

Curing of the coating can be extended at lower temperatures, dependent on coating thickness, substrate and texture.



## PREPARATION

- > The surface must be clean and dry (not damp).
- > Do not apply if surface is damp, wet or frosty.
- > The recommended surface temperature is +5°C to +30°C.
- > Application outside these limits will result in adhesion failure of the coating.
- > The surface should be free from loose or flaking material, dirt, grease and vegetative growth.
- > Vacuum or pressure blasting with air or water may remove any debris.
- > Brushing (manual or machine) may be suitable.
- > Friable, porous or aged concrete should be stabilised with a coating of Decatone Tarmac Binder prior to colour coating.

## APPLICATION

Surfaces that are cold – below 5°C– are not suitable for coating. Hot surfaces – above 30°C – should be cooled with water spray before application otherwise paint will dry before film formation is completed. New bitumen should be left to harden off before coating. The time will vary with the nature of the surface and the weather. (Minimum 3 weeks in summer and up to 3 months in winter.) New concrete should be allowed to mature for several months before coating. Do not over-paint/seal court. Recommended application between March and October.

## CLEANING

- > Clean all equipment with water immediately after use.

## PRECAUTIONS

- > The laying process requires the wearing of gloves, overalls and wellington boots to protect skin and clothes.
- > Remove dry paint from skin with a proprietary type cleaner and replace skin oils with a lanolin cream.
- > Eyes should be protected from splashes by the wearing of suitable goggles or visors.
- > Where the eyes are accidentally splashed they should be irrigated thoroughly with cold water and medical advice sought.
- > Protect from frost.
- > Do not apply paint if there is a risk of heavy rain or frost.
- > Do not use near fishponds.

## DO NOT LEAVE SITE WITHOUT CHECKING THAT THE COATING HAS FULLY CURED.

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability.

*As Britannia Paints Limited has no direct control over the methods employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself.*

If in doubt regarding any of the above points, please contact our technical services department for advice.

**A Material Safety Data Sheet is available on request.**

*It is the users responsibility to ensure that this data sheet is current prior to using the product.*



Cert: 8516



Materials and Suppliers Group



Unit 7/8 King Street Trading Estate, Middlewich, Cheshire CW10 9LF  
T: 01606 834015 F: 01606 837006 E: sales@britanniapaints.co.uk www.britanniapaints.co.uk

Version 13 / Dec 2010