

# MINI KIDS ZONE PAINT

## SR60 TENNIS COURT PAINT

Part of the junior club vision programme

### DESCRIPTION

A high quality water based Acrylic coating with slip-resistant properties for porous tennis courts. Bright colours used for the further enjoyment of tennis by juniors.

### USES

Formulated to give minimum slip on macadam and concrete tennis courts.

> For airless spray application.

**Power floated concrete areas as well as chemically or mechanically hardened floors may not be suitable for coating.**

### COLOUR RANGE

Available in Red (RAL 3020), Blue (RAL 5017) and Summer Tan (RAL 1019).

### PACK SIZE

> Available in 20 litre drums.

### SPREADING RATE

Painting may be carried out by most industrial airless equipment. Tip size of 28 thou is recommended with 45° angle. Thinning of up to 10% may be required. Care should be taken to mask all areas not to be coated.

> Coverage 6-8 square metres per litre per coat.  
Apply two coats.



### DRYING TIME

Drying takes from 1-2 hours in good conditions. Avoid painting in high humidity or when rain is expected. Over coating may be undertaken when first coat is dry to touch. Curing depends on atmospheric conditions. Please refer to specialist applicator recommendations regarding play after spraying is completed.

### SHELF LIFE

> Up to 12 months if stored correctly in an unopened container.  
> Store above 5°C.

### PREPARATION

All surfaces should be free from loose and flaking material, dirt, grease and vegetative growth. Any debris should be removed by vacuum or pressure blasting. Brushing (manual or machine) may be suitable in particularly difficult areas such as under trees or areas constantly in the shade. Decatone Tarmac Binder should be used to stabilise a friable, porous or aged concrete court or a fretting macadam court.



## APPLICATION

Surfaces that are cold – below 5°C – are not suitable for coating. Hot surfaces – above 30°C – should be cooled with water spray before application otherwise paint will dry before film formation is completed. New bitumen should be left to harden off before coating. The time will vary with the nature of the surface and the weather. (Minimum 3 weeks in summer and up to 3 months in winter.) New concrete should be allowed to mature for several months before coating. Do not over-paint/seal court. Recommended application between March and October.

Note. During the summer months there is a possibility of paint skinning from warm weather/transportation (top of inside rim). We recommend that the paint is pre-filtered on site through a course filter to remove skins before spraying.

## CLEANING

- > Clean all equipment with water immediately after use.

## PRECAUTIONS

- > Keep out of reach of children.
- > In case of contact with eyes wash immediately with plenty of water.
- > Remove splashes from skin with soap and water or a recognised hand cleaner.
- > Protect from freezing.
- > Do not apply paint if there is a risk of heavy rain or frost.
- > Do not use near fishponds.

## MAINTENANCE OF TENNIS COURT

To maintain the slip resistance of the coating, courts have to be regularly maintained and moss treated. Correct footwear must be worn. Do not apply salt or de-icer when surface is frozen.

## SITE CONDITIONS

Precautions must be taken and recommendations given to the client/club with regard to possible failure when courts are in a damp condition or when shaded by over-hanging trees or bushes. Trees and bushes produce residues, which can be deleterious and cause breakdown of the top layer of macadam. Guidelines are available from SAPCA and should be followed.

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability.

*As Britannia Paints Limited has no direct control over the methods employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself.*

If in doubt regarding any of the above points, please contact our technical services department for advice.

**A Material Safety Data Sheet is available on request.**

*It is the users responsibility to ensure that this data sheet is current prior to using the product.*



Cert: 8516



Materials and Suppliers Group



Unit 7/8 King Street Trading Estate, Middlewich, Cheshire CW10 9LF  
T: 01606 834015 F: 01606 837006 E: sales@britanniapaints.co.uk www.britanniapaints.co.uk

Version 12 / Dec 2010