

LINE MARKING PAINT

WATER BASED ACRYLIC COATING

LONG-LASTING OUTDOOR SPORTS SURFACE MARKING

PERFORMANCE ADVANTAGES

- > Deep penetration for long life
- > Available in thick brush-quality grade or for spray/roller application

USES

- > Suitable for lining of sports surfaces
- > Can be applied by Brush or special Spray/Roller machines

Power floated concrete areas as well as chemically or mechanically hardened floors may not be suitable for coating.

COLOUR RANGE

White, Yellow, Blue, Brick Red, Orange and selected colours.

PACK SIZE

- > Available in 5 litre and 20 litre containers.

SPREADING RATE

As a guide the coverage is between 35-70 linear metres per litre, at 50mm width, dependent on substrate, texture and porosity of the surface. Typically a tennis court will use a maximum of 5 litres.

DRYING TIME

Surface dry in 1-2 hours, re-coatable when dry. Avoid painting when rain is expected or under poor drying conditions – below 5°C.

SHELF LIFE

- > Up to 12 months if stored correctly in an unopened container.
- > Store above 5°C.



PREPARATION

All surfaces should be free from loose and flaking material, dirt, grease and vegetative growth. Any debris should be removed by vacuum or pressure blasting with air or water. Brushing (manual or machine) may be suitable in particularly difficult areas, i.e: under trees or areas constantly in the shade. Decatone Tarmac Binder should be used to stabilise a friable, porous or aged concrete court or fretting macadam.

APPLICATION

> STIR WELL BEFORE USE

By Brush or special Spray/Roller machines. Thinning up to 10% may be required. Surfaces that are cold – below 5°C – are not suitable for coating. Hot surfaces – above 30°C – should be cooled with water spray before application, otherwise paint will dry before film formation is completed. New bitumen should be left to harden off before coating. The time will vary with the nature of the surface and the weather. (Minimum 3 weeks in summer and up to 3 months in winter.) New concrete should be allowed to mature for several months before coating. Recommended application between March and October.



INITIAL PLAY ON THE SURFACE

- > After spraying, courts are usually left for one week before play recommences. At the beginning and towards the end of the summer season, when temperatures are cooler and surfaces take longer to dry, it is advisable to extend this period by a few days, depending on the prevailing weather.
- > Optimum slip resistance is only achieved between two and three weeks after spraying. This is because the court surface has to bed in with use.

SITE MAINTENANCE

To maintain the slip resistance of the Line Marking Paint it should be regularly maintained and moss treated. Correct footwear must be worn. Do not apply salt or de-icer when surface is frozen. Detailed guidance on the maintenance of painted courts may be found in SAPCA's code of practice for the Maintenance of Synthetic Sports Surfaces at (www.sapca.org.uk).

CLEANING

- > Clean all equipment with water immediately after use.

PRECAUTIONS

- > Keep out of reach of children.
- > In case of contact with eyes wash immediately with plenty of water.
- > Remove splashes from skin with soap and water or recognised hand cleaner.
- > Protect from freezing.
- > Do not use near fishponds.

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability.

As Britannia Paints Limited has no direct control over the methods employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself.

If in doubt regarding any of the above points, please contact our technical services department for advice.

A Material Safety Data Sheet is available on request.

It is the users responsibility to ensure that this data sheet is current prior to using the product.



Certificate Number 8516
ISO 9001



Unit 7/8 King Street Trading Estate, Middlewich, Cheshire CW10 9LF
T: 01606 834015 F: 01606 837006 E: sales@britanniapaints.co.uk www.britanniapaints.co.uk

Version 15 / Apr 2020